

DIN NF EN 10088	Ex Afnor	Werkstoff	AISI	BS	Divers
X10NiCrAlTi32-20	Z8NC33-21	1.4876	B163 / B425	3076 / NA15H	Inconel 800HT
X8NiCrAlTi32-21		1.4959			Alloy 800HT
X2NiCoMo18.8.5	E-Z2NKD18	1.6359		S162	Marval 18
CuNi10Fe1Mn		2.0872			90/10
Ni99,2	NI99.2	2.4060	B160	3072	Nickel 200
NiCu30Fe	NU30	2.4360	B164 / B127	3075/6NA13	Monel400
NiCu30Fe	NU30m	2.4360	B164/B165	•	Monel 400
NiCu30Al	NU30AT	2.4375	B127	3075/6NA18	Monel K500
NiMo28 NiMo29Cr	•	2.4600	B622	•	Alloy B3/ Hastelloy B2
NiCr21Mo14W		2.4602	B619		Hastelloy C22
NiCr30FeMo		2.4603			Hastelloy G30
NiCr23Mo16Al		2.4605			Alloy 59
NiMo16Cr16Ti		2.4610			Hastelloy C4
NiMo28		2.4617			Hastelloy B2
NiCr22Mo6Cu		2.4618			Hastelloy G
NiCr22Mo7Cu		2.4619			Hastelloy G30
NiCr20Ti		2.4630			Nimonic 75
NiCr20TiAl	NICR20TIAL	2.4631		HR1/HR201	Nimonic 80A
NiCr20Co18Ti	6NA19	2.4632	AISI 5829	HR501/2/3/307	Nimonic 90
NiCr25FeAl		2.4633			Alloy 602 CA
NiCo20Cr15Mo		2.4634			Nimonic 105
NiCr29Fe		2.4642			Alloy 690
Alloy 20		2.4660	B473		Alloy 20
NiCr23Co12Mo		2.4663			Inconel 617
NiCr22Fe18Mo		2.4665			Hastelloy X
NiCr19NbMo		2.4668			Inconel 718
NiCr15Fe7TiAl		2.4669	B637/AMS 5699	HR505	Inconel X750
NiCr60-15		2.4687			60/15
NiCr19NbMo	NC19FeNb	2.4688	AMS 5662		
NiCr22W14Mo	•	2.4733	B435/AMS 5878		Haynes 230
CoCr28		2.4778			Umco 50
NiCr15Fe	NC15FE	2.4816	B166/ 168/ B163	3075/6NA14	Alloy 600
NiMo16Cr15W	•	2.4819	B574/B575	•	Hastelloy C276
NiCr23Fe		2.4851			Inconel 601
NiCr22Mo9Nb	NC22DNb	2.4856	B443/B446		Inconel 625
NiCr21Mo	NFe32C20DU	2.4858	B425 / B424	3076NA16	Inconel 825
NiCr80-20		2.4869			80/20



FILA SAS
 ZA La Forêt - 44830 Bouaye
 Tél. 02 51 70 51 51 - Fax 02 40 65 41 62
 Web. www.fila-sa.com