

DIN NF EN 10088	Ex Afnor	Werkstoff	ASTM/SAE	BS	Divers
AL99.5	1050A/A5/A5	3.0255	1050	1050A	
AlMn		3.0515		N3	
AlCu4MgSi	2017A	3.1325	2017A/AMS 4118	2017A	
AlCuMg1	A-U4G1	3.1355	2024	L97	
AlCu4PbPg	2030	3.1645	2030		DURALUNIN
AlCu6BiPb	A-U5PbBi	3.1655	2011	2011/FC1	AW-ALCU6BiPb
AlMgSi1		3.2315	6351	H30	
AlMgSi0,5		3.3206	6063	H9	
AlMg1	A-G0,6	3.3315	5005	N41	
AlMg1,5	A-G1,5	3.3316	5050	3L44	
AlMg2,5	A-G2,5C	3.3523	5052	2L56	
AlMg3	A-G3M	3.3535	5754	N5	
AlMg3	AG3T	3.3541			
AlMg4Mn	A-G4MC	3.3545	5086		
AlMg4	5083	3.3547	50832	5083/N8	Coulé
AlMg5		3.3549	5056	N6	
AlZnMgCu1.5	7075/AZ5GU	3.4365	7075	7075/DTD5074	FORTAL
AlZnMg1				7005	
AlMg2,5Mn	A-G2,5MC		5454	N51	



Fila SAS

ZA La Forêt - 44830 Bouaye

Tél. 02 51 70 51 51 - Fax. 02 40 65 41 620

Web. www.fila-sa.com - Email. commercial@fila-sa.com